

Media Thickness 0.1mm
 Media Width 30"/54"/60"
 Media Length 150'
 Media Weight (g/m²) 295g ± 5%

The properties of raw material	Description/Unit	Specification
Substrate	Base	PVC
	Thickness	4mil
	Gloss level	Gloss
Adhesive	Type	Solvent Arcylic
	Thickness	0.3mm
	Colour	Clear
	Temp range	°20 C ~ +°60 C
	Water proof level	Water Proof
Liner	Weight of Release paper	0.036mm, PET

The properties of raw material	Description/Unit	TSET DATA	CRITERIA	TEST METHOD
Tensile Strength (kg/m²)	MD	322	≥ 250	ASTM-D-882A
	CD	284	≥ 220	
Enlongation (%)	MD	198	≥ 130	ASTM-D-882A
	CD	198	≥ 130	
100% MOD (kg/cm²) Modulus at 100%	MD	234	≥ 170	ASTM-D-882A
	CD	215	≥ 160	
Tear Resistion (kg/mm)	MD	10.1	≥ 9	ASTM-D-1004
	CD	9.5	≥ 9	
Dimensional Stability (%)	MD	3.4	≤ 5.5	ASTM-D-1204
Thickness (mm)		0.0791	0.08 ± 0.01	ASTM-D-1593
Durability	Year	2 Year		
Water proof level	<input checked="" type="checkbox"/> Water Proof <input type="checkbox"/> Water Resistance <input type="checkbox"/> Non water Resistance			
Remark:	<input type="checkbox"/> ROHS Approval (Restiction Of Hazard Substance)			